

Optical and Mechanical Properties of Nano-Composite Optical Ceramics

***C. Scott Nordahl, Thomas Hartnett, Todd Gattuso, Richard Gentilman**
Raytheon Integrated Defense Systems
c_scott_nordahl@raytheon.com

Submicron and Nanostructured Ceramics

10 June, 2009



DARPA Distribution Statement "A"
Approved for Public Release, Distribution Unlimited
Copyright © 2009 Raytheon Company. All rights reserved.

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE JUN 2010		2. REPORT TYPE N/A		3. DATES COVERED -	
4. TITLE AND SUBTITLE Optical and Mechanical Properties of Nano-Composite Optical Ceramics				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Raytheon Integrated Defense Systems				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release, distribution unlimited					
13. SUPPLEMENTARY NOTES See also ADM002307. ECI International Conference on Sub-Micron and Nanostructured Ceramics Held in Colorado Springs, Colorado on 7-12 June 2009, The original document contains color images.					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 21	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

Introduction

Raytheon
Integrated Defense Systems

- **Background**
 - Current MWIR transparent materials
 - Nano-composite oxides
- **Processing/Microstructures**
- **Optical Properties**
- **Mechanical Properties**
- **Summary**



DARPA Distribution Statement "A"
Approved for Public Release, Distribution Unlimited
Copyright © 2009 Raytheon Company. All rights reserved.

Acknowledgements

Raytheon
Integrated Defense Systems

Funded by DARPA under Contract N00014-07-C-0337


Sharon Beermann-Curtin / Bill Coblenz, DARPA Program Managers

Raytheon NCOC Project Team

Raytheon IDS	-	Scott Nordahl
Raytheon RMS	-	Brian Zelinski
Amastan	-	Kamal Hadidi
CeraNova	-	Mark Parish
Nanocerox	-	Todd Stefanik
Rutgers	-	Bernie Kear
UC-Davis	-	Amiya Muhkerjee
UConn	-	Eric Jordon

Raytheon
Missile Systems

nanocerox



DARPA Distribution Statement "A"
Approved for Public Release, Distribution Unlimited
Copyright © 2009 Raytheon Company. All rights reserved.

Maximizing the Optical and Mechanical Performance

Raytheon
Integrated Defense Systems

The goal is to achieve all of the following simultaneously:

DARPA Goals:

- High Strength - equivalent to Sapphire
- Scaleable Method - able to produce 3” domes
- MWIR Transparent - equivalent to Spinel

Raytheon “Stretch Goal”

- MWIR Transparency - equivalent to Yttria


To achieve these goals:

- No pore phase (large $\Delta n \sim 0.8$ = scatter)
- Minimize grain size / grain growth ($G.S. \leq \lambda/20$ for transparency)
- Uniform 2-phase microstructure (small $\Delta n < 0.2$)
- Avoid MWIR absorptions due to Si-O and Al-O bonds



DARPA Distribution Statement “A”
Approved for Public Release, Distribution Unlimited
Copyright © 2009 Raytheon Company. All rights reserved.

Project Approaches



Background


















































Sapphire (single crystal Al_2O_3) is the current MWIR dome material of choice.

- High strength
- Excellent erosion durability (rain/sand)
- High thermal shock resistance
- Low optical scatter
- Intrinsic birefringence
- Lacks full 3-5 μm transparency (absorption at 5 μm)
- Significant MWIR emission at elevated/operating temperatures
- High temperature mechanical properties degradation
- High cost due to single crystal growth and optical finishing










Objective:

Make much stronger dome materials and retain full MWIR transmittance

	Optical Properties			Mechanical Properties			
	Absorption	Scatter	Optical Isotropy	Mech. Strength	Impact Resist.	Thermal Shock Resist.	Machinability
Sapphire							
Spinel							
ALON							
Y ₂ O ₃							
MgO							
ZrO ₂							
YAG							

	Excellent
	Marginal
	Poor



	Absorption	Scatter	Optical Isotropy	Mech. Strength	Impact Resist.	Thermal Shock Resist.	Machinability
Oxide Nano-Composites							



Maximizing the Optical Performance

Problem: Most durable MWIR dome materials contain Al-O bonds. However, Al-O bonds absorb at $\lambda > 4$ microns

Solution: Select nanocomposite systems without Al-O bonds (Y_2O_3 , MgO , ZrO_2)






DARPA Distribution Statement "A"
Approved for Public Release, Distribution Unlimited

Copyright © 2009 Raytheon Company. All rights reserved.

Nanocomposite Composition

Baseline Material System: Yttria : Magnesia

$\text{Y}_2\text{O}_3:\text{MgO}$
20:80 Mol% \rightarrow $\text{Y}_2\text{O}_3:\text{MgO}$
50:50 Vol%



Nanocomposite Optical Ceramics:

A new class of MWIR dome materials

Approach: *Reduce grain size* of transparent polycrystalline ceramics to *increase strength*:



Hall Petch relation: $\sigma \propto (\text{g.s.})^{-1/2}$

Problem: Processing conditions (high T & P) required to densify to optical clarity promote grain growth

Solution: Use significant volume fractions of two or more mutually insoluble transparent ceramics (e.g. $\text{MgO} + \text{Y}_2\text{O}_3$)


Problem: Refractive index differences between phases cause scattering by the grains

Solution: Reducing the grain size to $< \lambda/20$ eliminates scatter and transparency is restored:
 $4\mu\text{m}/20 = 200 \text{ nanometers !}$



Nanopowder Production via Liquid Flame Spray Pyrolysis

Raytheon
Integrated Defense Systems




DARPA Distribution Statement "A"
Approved for Public Release, Distribution Unlimited
Copyright © 2009 Raytheon Company. All rights reserved.

Process Overview

Powder Process



- Starting powders produced by Flame Spray Pyrolysis
- Densified by Sinter + HIP
- Slip Casting – alternate forming method
- SPS densification – smaller grain size



Nanocomposite Microstructure

Raytheon
Integrated Defense Systems

Backscattered electron images.
50:50 Vol% Yttria:Magnesia



Uniform microstructure with ~150nm grain size.




DARPA Distribution Statement "A"
Approved for Public Release, Distribution Unlimited
Copyright © 2009 Raytheon Company. All rights reserved.

Optical Properties



Raytheon
Integrated Defense Systems

MgO:Y₂O₃ Nanocomposites

In the visible band





In the MWIR band



DARPA Distribution Statement "A"
Approved for Public Release, Distribution Unlimited
Copyright © 2009 Raytheon Company. All rights reserved.

Powder Process Optimization

Raytheon
Integrated Defense Systems



- Fracture strength improved with optimized powders and processing.
- New material systems and/or more energetic processing needed for 1200 MPa!



DARPA Distribution Statement "A"
Approved for Public Release, Distribution Unlimited
Copyright © 2009 Raytheon Company. All rights reserved.


Material Property Goals

Material Property Metrics for 3-5 micron Nano-Composite Optical Ceramics

Material Property	Units	Phase I Metrics	Achieved	Phase II Metrics
Absorption Coefficient (ave, 3-5 μ m)	cm ⁻¹	≤ 0.1	0.05	≤ 0.1
Optical Scatter (Fwd TIS @ 3.39 μ m)	%	≤ 2.0	0.6	≤ 0.5
Fracture Strength at 600°C (average of 10 biaxial disks)	MPa	≥ 600	650	≥ 1200
Hardness (μ -indent: 50g load)	kg/mm ²	≥ 2200	2350	≥ 2200
Thermal Shock Resistance (requires thermal conductivity measurement)	calculated FoM: R'	- - -	1.3 X Sapphire	$\geq 2X$ Sapphire
Sand Erosion Resistance (blowing sand – conditions TBD)	grams/std test	- - -		$\geq 2X$ Sapphire
Water Drop Threshold Velocity (Marshall SFC – 3mm drop)	m/s	- - -		$\geq 2X$ Sapphire




Spark Plasma Sintering




Spark Plasma Sintering


Modeling die geometries to improve temperature uniformity in scaled-up process



3" Diameter Disk




Uniform Microstructure





Direct Deposition

Raytheon
Integrated Defense Systems






DARPA Distribution Statement "A"
Approved for Public Release, Distribution Unlimited
Copyright © 2009 Raytheon Company. All rights reserved.



Direct Deposition

Raytheon
Integrated Defense Systems

50:50 MgO:Y₂O₃



DARPA Distribution Statement "A"
Approved for Public Release, Distribution Unlimited
Copyright © 2009 Raytheon Company. All rights reserved.

Summary

- **MgO:Y₂O₃ based nanocomposite ceramics have been developed using traditional ceramic processing routes and demonstrated:**
 - **Sapphire equivalent mechanical durability**
 - **Yttria equivalent MWIR optical transparency**
- **New nanocomposite material systems show potential for greater mechanical durability with inherently more durable crystallographic phases.**
- **More energetic fabrication techniques are showing promise for refined microstructures and improved mechanical properties.**

